

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
14 October 2004 (14.10.2004)

PCT

(10) International Publication Number
WO 2004/087310 A1

- (51) International Patent Classification⁷: **B01J 21/06**, 21/16, 29/04, 27/18, C07D 213/00
- (21) International Application Number: PCT/IN2003/000101
- (22) International Filing Date: 31 March 2003 (31.03.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (71) Applicant: **COUNCIL OF SCIENTIFIC AND INDUSTRIAL RESEARCH [IN/IN]**; Rafi Marg, New Delhi 110 001 (IN).
- (72) Inventors: **ROY, Shyam, Kishore**; Central Fuel Research Institute, P.O.F.R.I., Dhanbad, Jharkhand (IN). **ROY, Subhash, Chandra**; Central Fuel Research Institute, P.O.F.R.I., Dhanbad, Jharkhand (IN). **DUTTA, Pasupati**; Central Fuel Research Institute, P.O.F.R.I., Dhanbad, Jharkhand (IN). **NANDI, Laxmi, Narayan**; Central Fuel Research Institute, P.O.F.R.I., Dhanbad, Jharkhand (IN). **YADAV, Satya, Niketan**; Central Fuel Research Institute, P.O.F.R.I., Dhanbad, Jharkhand (IN).
- (74) Agents: **SUBRAMANIAM, Hariharan** et al.; Subramaniam, Nataraj & Associates, E-556 Greater Kailash II, New Delhi 110 048, Maharashtra (IN).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: TI-PILLARED CLAY BASED VANDIA CATALYST AND PROCESS FOR PREPARATION

(57) Abstract: This invention relates to a process for the preparation of highly active and selective ammoxidation catalyst using a complex metal oxide containing P, V and Mo supported on Ti-PILC which process involves heating on water bath a vanadium source with oxalic acid in the presence of water to form vanadyl oxalate; adding a source of phosphorous and a source of Mo and Ti-PILC and heating the resultant mixture in the presence of air at a temperature in the range of 110-450°C for a period in the range of 15 to 35 h and the use of said ammoxidation catalyst in the preparation of heteroaromatic nitriles from methyl pyridines which comprises passing as a reactant stream a gaseous mixture comprising, a methyl substituted pyridine, ammonia and oxygen (air) over the fixed bed ammoxidation catalyst at a temperature of about 350 - 450°C.

WO 2004/087310 A1

TI-PILLARED CLAY BASED VANADIA CATALYST AND PROCESS FOR PREPARATION

Field of the invention

5 The invention relates to a pillared clay based vanadia catalyst. The present invention also relates to a process for the preparation of vanadia based catalyst supported on titanium-pillared clay useful for producing heteroaromatic nitriles. The present invention also relates to a process for the preparation of pillared clay based vanadia catalyst useful for production of nicotinonitrile (3-cyanopyridine) by ammoxidation of 3-picoline and to the use thereof for
10 the production of 3-cyanopyridine.

Background of the invention

 The present invention finds its usage in preparing valuable intermediates for the preparation of corresponding amides, which are used in pharmaceuticals. 3-cyano-pyridine is used in the preparation of niacin, used for the treatment of pellagra. Many drugs based on
15 niacin have curative effects such as lowering the limit of cholesterol and free fatty acids in blood, stimulation of the respiratory apparatus, antispasmodic and anti-rheumatic action e.g. the antispasmodic lyspamin and coramine or Nikethamide and Bilamid used in treating infections of gallbladder or bile duct.

 Reference is made to US Patent 5,614,453 which relates to acid catalyzed chemical
20 conversion processes, such as hydrocarbon conversion processes, and to the catalysts and catalyst supports used in such processes. The invention is particularly concerned with catalyst supports containing a combination of zeolite Beta and a pillared clay, catalysts comprising such supports and the use of such catalysts in hydrocarbon conversion processes, particularly hydrocracking. There is no mention about conversion of 3-picoline. Reference is also made to
25 US Patents 2,510,605, 2,839,535 and 2,861,999 wherein the catalysts based on vanadium, molybdenum and phosphorous on activated alumina has been described. However, the yields of nicotinonitrile and isonicotinonitrile were in the range of 60 to 70 %. Reference is also made to US Patent 3981879 wherein catalysts based on vanadium, molybdenum, phosphorous oxides and tin oxide over pumice have been described which gives 90%
30 selectivity at 76% conversion. Reference is also made to Japanese Patent 19706 wherein a catalyst has been disclosed, comprising of antimony oxide, vanadium oxide containing a metal from group (iron, copper, titanium, cobalt, manganese and nickel with high selectivity but it deactivates due to reduction by ammonia.

 Pillared clays are typically prepared by reacting a smectite clay such as
35 montmorillonite, saponite, hectorite, and beidellite with a pillaring agent or propping agent to

form a flocculated reaction product which is subsequently dried to convert the pillaring agent into inorganic metal oxide clusters which form the pillars which prop apart the layers of the clay. The X-ray diffraction pattern of a pillared clay normally contains a distinct first order reflection which is indicative of a well ordered, long range, face-to-face orientation of the clay platelets.

Prior art search for a process for preparation of titanium based pillared clay catalyst for conversion of 3-picoline to 3-cyanopyridine has been made based on literature survey and patent databases, which did not yield any relevant references.

Objects of the invention

The main object of the present invention is to provide a process for the preparation of a catalyst supported on titanium-pillared clay useful for producing heteroaromatic nitriles.

Another object of the present invention is to provide a process for the preparation of pillared clay based vanadia catalyst useful for production of nicotinonitrile (3-cyanopyridine) by ammoxidation of 3-picoline.

Yet another object of the present invention is to convert 3-picoline into nicotinonitrile in a single step reaction between 3-picoline, ammonia and air.

Still another object of the present invention is to provide a process for preparing 3-cyano pyridine in high yield (>90%).

Summary of the invention

Accordingly the present invention provides a pillared clay based vanadia catalyst useful for the conversion of 3-picoline to 3-cyanopyridine, said catalyst comprising vanadium, phosphorous and molybdenum on a Ti-pillared clay support.

In one embodiment of the invention, the clay is pillared with polyoxymetal cations of titanium and has titania clusters as the pillars between the layers.

In another embodiment of the invention, the clay is selected from a single smectite clay and mixed layer smectite clays.

In another embodiment of the invention, the single smectite clay comprises montmorillonite clay.

In another embodiment of the invention, the mixed layered smectite clay is selected from rectorite and paragonite.

In another embodiment, the pillared clay contains a homogeneous distribution of pillars in the interlayered spaces thereof forming an array of rectangular openings or pores of a size in the range of 7 to 20 Angstroms high and between 8 and 20 Angstroms wide, enabling the pillared clay to perform like a two-dimensional crystalline molecular sieve.

In still another embodiment of the invention the ratio of the compounds of vanadium, molybdenum, phosphorous over titanium pillared clay in the catalyst is in a ratio ranging between 1.0: 2.5: 0.5: 20 - 1.0: 30: 1.5: 50.

5 In a further embodiment of the invention, the pillared clay contains one or more rare earth elements selected from cerium, lanthanum and a mixture thereof.

The present invention also relates to a process for the preparation of a pillared clay based vandia catalyst comprising first preparing vanadyl oxalate by heating a vanadium rich compound on a water bath followed by addition of oxalic acid till the colour of the mass changes to violet blue indicating the formation of vanadyl oxalate, said vanadyl oxalate being
10 in dilute solution, adding a phosphorous source to the dilute solution of vanadyl oxalate heated over water bath, followed by addition of an aqueous solution of molybdenum source and mixing while adding a Titanium source under stirring, evaporating the solution over water bath till the mass is reduced to about half, further heating the mass till a powder catalyst is obtained.

15 In an embodiment of the present invention vanadium rich compound is selected from the group consisting of ammonium metavanadate, vanadyl sulphate and oxides of vanadium.

In another embodiment, the oxide of vanadium is vanadium pentoxide.

In another embodiment of the invention the phosphorous source is selected from the group consisting of ortho-phosphoric acid, pyro-phosphoric acid and meta-phosphoric acid.

20 In yet another embodiment the molybdenum source is ammonium molybdate.

In another embodiment of the invention the titanium source is titanium-pillared clay.

In one embodiment of the invention, the clay is pillared with polyoxymetal cations of titanium and has titania clusters as the pillars between the layers.

25 In another embodiment of the invention, the clay is selected from a single smectite clay and mixed layer smectite clays.

In another embodiment of the invention, the single smectite clay comprises montmorillonite clay.

In another embodiment of the invention, the mixed layered smectite clay is selected from rectorite and paragonite.

30 In a further embodiment of the invention, the pillared clay contains one or more rare earth elements selected from cerium, lanthanum and a mixture thereof.

In another embodiment of the invention the ratio of the compounds of vanadium, molybdenum, phosphorous over titanium pillared clay in the catalyst is in a ratio ranging between 1.0: 2.5: 0.5: 20 - 1.0: 30: 1.5: 50.

In a further embodiment of the invention, the pillared clay contains one or more rare earth elements selected from cerium, lanthanum and a mixture thereof.

In still another embodiment of the invention the ratio of the compounds of vanadium, molybdenum, phosphorous over titanium pillared clay in the catalyst is in a ratio ranging
5 between 1.0: 2.5: 0.5: 20 - 1.0: 30: 1.5: 50.

In another embodiment of the invention, the pillared clay contains a homogeneous distribution of pillars in the interlayered spaces thereof forming an array of rectangular openings or pores of a size in the range of 7 to 20 Angstroms high and between 8 and 20 Angstroms wide, enabling the pillared clay to perform like a two-dimensional crystalline
10 molecular sieve.

Detailed description of the invention

The novelty of the present invention lies in providing a catalyst for conversion of 3-picoline to 3-cyanopyridine by reaction of ammonia and air with 3-picoline in a single step, yielding a high purity product, eliminating expensive oxidising agents and enabling the
15 operation of the process on a continuous basis and the inventive step lies in providing non-obvious steps of the process in an environmental friendly manner in comparison to prior art processes.

A preferred pillared clay for use in the catalyst of the invention has been pillared with polyoxymetal cations of titanium and therefore has titania clusters as the pillars between the
20 layers. Besides a single smectite clay such as montmorillonite, mixed layered smectites such as rectorite and paragonite can also be pillared and used in the catalyst of the invention. Examples of pillared clays which possess stability at high temperatures are ones in which the pillars contain one or more rare earth elements such as cerium and/or lanthanum. Such clays are disclosed in U.S. Pat. Nos. 4,753,909 and 4,952,544 and in PCT International Application
25 WO 88/06614, the disclosures of which patents and application are hereby incorporated by reference in their entirety.

It will be understood, however, that pillared clays in which the pillars are substantially free of rare earth elements can be used as a component of the catalyst. Pillared clays and their preparation are described generally in an article entitled "Intercalated Clay Catalysts,"
30 Science, Vol. 220, No. 4595, pp. 365-371 (Apr. 22, 1983), the disclosure of which is hereby incorporated by reference in its entirety.

The following examples are given by way of illustration of the present invention and should not be construed to limit the scope of the present invention.

Example 1

Preparation of Ti-Pillared clay: TiO_2 - PILC (Titanium pillared clay) was synthesized by pillaring montmorillonite /bentonite clay (sodium ion exchanged) by a solution of partially hydrolysed Ti-polycations. Ti-polycation was prepared by adding the concentrated solution of TiCl_4 into 2 moles of HCl(Hydrochloric Acid). The mixture was then diluted by slowly adding water with constant stirring so that final concentration of Titanium in the solution was 0.82 mole and final concentration of HCl was 0.6 mole.

8 g Sodium exchanged clay was dispersed in 2 litre distilled water. The slurry was stirred for 8 h by mechanical stirrer. The Titanium polycation pillaring agent was added to the slurry slowly with vigorous stirring at 90°C . The solution contained 10 m mole titanium/g clay. The resulting solution was further stirred for 4 h. The solution was kept 18 h at room temperature. The mass was filtered under suction and thoroughly washed with distilled water to make chloride ion free. The product is oven dried at $110\pm 10^\circ\text{C}$ for 6 h. Finally it was calcined at 350°C for 12 h in a muffle furnace.

Preparation of Vanadyl oxalate: 45 g vanadium pentoxide in water(1:5) was heated over steam bath and 122 g oxalic acid crystals slowly added pinch wise with stirring till the colour of the slurry changes from yellow to violet blue. It was further heated over steam bath for 15 minutes. Thus the solution of vanadyl oxalate was prepared.

Preparation of the catalyst and its use in ammoxidation of 3-picoline: 6.6 ml vanadyl oxalate solution containing 3.1 g vanadyl oxalate (equivalent to 1.8 g vanadium pentoxide) as prepared above was taken in a porcelain basin. It was diluted with 40 ml of distilled water, mixed thoroughly with stirring and heated at $70-80^\circ\text{C}$. To this solution 0.05 g H_3PO_4 (85%) was added and mixed thoroughly. Another solution was made using 0.4 g molybdenum trioxide and 5 ml of (1:1) ammonium hydroxide and heated at $70-80^\circ\text{C}$. Both the solutions were mixed with stirring at the same temperature. 7.75 g Ti-PILC was added to the mixed solution with constant stirring. It was stirred for another 15 minutes. The mixed mass was heated on a steam bath. This was then heated in an air oven at 110°C for 15 h, then in a muffle furnace for 3 h at 300°C and further at 425°C for 15 h. The powder catalyst was pelletized and used in the form of -6 to +14 BS mesh.

The reaction was carried out using a down flow, fixed bed, pyrex glass reactor of 20 mm i.d.. The reactor is packed with 10 ml (8 g) Ti-PILC based catalyst. The reaction mixture was fed from top of the reactor. 3-Picoline and water in the ratio 1:3 (by vol) was fed at the rate 4.35 ml/h using a syringe pump (Sage instrument). Ammonia gas(2.1 l/h) from gas cylinder and air (4.5 l/h) through calibrated flow meter were fed in to the reactor. The

reaction was carried out at temperature of $425 \pm 10^{\circ}\text{C}$ and contact time 1.4 s (space velocity 2571 cc/cc cat/h). The product was cooled using ice cooled water and collected at the bottom followed by two number of ice traps. The product was analysed by gas chromatograph using 2 m length carbowax 20 M column at 160°C temperature and Thermal Conductivity Detector.

5 The yield of the product (3-cyanopyridine) was 80.6% where as the conversion of 3-picoline was 87.6 %

Example 2

Preparation of Ti-Pillared clay: TiO_2 - PILC (Titanium pillared clay) was synthesised by pillaring montmorillonite /bentonite clay (sodium ion exchanged) by a solution of partially hydrolysed Ti-polycations. Ti-polycation was prepared by adding the concentrated solution

10 of TiCl_4 into 2 moles of HCl(Hydrochloric Acid). The mixture was then diluted by slowly adding water with constant stirring so that final concentration of Titanium in the solution was 0.82 mole and final concentration of HCl was 0.6 mole.

8 g Sodium exchanged clay was dispersed in 2 litre distilled water. The slurry was

15 stirred for 8 h by mechanical stirrer. The Titanium polycation pillaring agent was added to the slurry slowly with vigorous stirring at 90°C . The solution contained 10 m mole titanium/g clay. The resulting solution was further stirred for 4 h. The solution was kept 18 h at room temperature. The mass was filtered under suction and thoroughly washed with distilled water to make Cl^- ion free. The product is oven dried at $110 \pm 10^{\circ}\text{C}$ for 6 h. Finally it was calcined at

20 350°C for 12 h in a muffle furnace.

Preparation of Vanadyl oxalate: 45 g vanadium pentoxide in water(1:5) was heated over steam bath and 122 g oxalic acid crystals slowly added pinch wise with stirring till the colour of the slurry changes from yellow to violet blue. It was further heated over steam bath for 15 minutes. Thus the solution of vanadyl oxalate was prepared.

8.9 ml vanadyl oxalate solution containing 3.1 g vanadyl oxalate (equivalent to 1.8 g vanadium pentoxide) was taken in a porcelain basin. It was diluted with 40 ml of distilled water, mixed thoroughly with stirring and heated at $70\text{--}80^{\circ}\text{C}$. To this solution 0.1 g H_3PO_4 (85%) was added and mixed. Another solution was made using 0.4 g molybdenum trioxide and 5 ml of (1:1) ammonium hydroxide and heated to $70\text{--}80^{\circ}\text{C}$. This solution was added to

25 the first solution with stirring keeping the temperature at about 80°C . 7.75 g Ti-PILC was added to the mixed solution with constant stirring. It was stirred for another 15 minutes. The mixed mass was evaporated on a steam bath. This was then oven dried at $110\text{--}120^{\circ}\text{C}$ for 15 h, then calcined in a muffle furnace for 3 h at 300°C and further at 425°C for 15 h. The powder catalyst was pelletised and used in the form of -6 to +14 BS mesh.

30

The reaction was carried out using a down flow fixed bed pyrex glass reactor of 20 mm i.d. The reactor was packed with 5 ml (4.38 g) Ti-PILC based catalyst. The reaction mixture was fed from the top of the reactor 3-picoline and water in the ratio of 1:3 by vol. was fed at the rate of 4.3 ml/h using a syringe pump (Sage instrument). Ammonia gas (2.10 l/h) and air (4.5 l/h) from cylinder through calibrated flow meter were fed into the reactor. The reaction was carried out at temperature 440 ± 10 °C and contact time 0.66 s (space velocity 5438-cc/cc cat/h). The yield obtained was 91% conversion 98.0 %.

Example 3

Preparation of Ti-Pillared clay: TiO_2 - PILC (Titanium pillared clay) was synthesised by pillaring montmorillonite /bentonite clay (sodium ion exchanged) by a solution of partially hydrolysed Ti-polycations. Ti-polycation was prepared by adding the concentrated solution of TiCl_4 into 2 moles of HCl (Hydrochloric Acid). The mixture was then diluted by slowly adding water with constant stirring so that final concentration of Titanium in the solution was 0.82 mole and final concentration of HCl was 0.6 mole.

8 g Sodium exchanged clay was dispersed in 2 litre distilled water. The slurry was stirred for 8 h by mechanical stirrer. The Titanium polycation pillaring agent was added to the slurry slowly with vigorous stirring at 90°C. The solution contained 10 m mole titanium/g clay. The resulting solution was further stirred for 4 h. The solution was kept 18 h at room temperature. The mass was filtered under suction and thoroughly washed with distilled water to make Cl^- ion free. The product is oven dried at 110 ± 10 °C for 6 h. Finally it was calcined at 350°C for 12 h in a muffle furnace.

Preparation of Vanadyl oxalate: 45 g vanadium pentoxide in water(1:5) was heated over steam bath and 122 g oxalic acid crystals slowly added pinch wise with stirring till the colour of the slurry changes from yellow to violet blue. It was further heated over steam bath for 15 minutes. Thus the solution of vanadyl oxalate was prepared.

Solution A was prepared by diluting 18 ml vanadyl oxalate solution containing 9.35 g vanadyl oxalate(equivalent to 5.49 g vanadium pentoxide) with 75 g distilled water and 0.95 g H_3PO_4 (85%) was added and mixed. Solution B was prepared by dissolving 17.6 g ammonium hepta molybdate in 65 g distilled water. Both solutions were heated at 70-80 °C, solution A was added to solution B and 10.5 g Ti-pillared clay was added and mixed thoroughly. This mixed mass was then heated over steam bath till the mass reduced to about half. Semi dried mass of the catalyst was then oven dried at 110-120 °C for 15 h and then calcined at 300 °C for 3 hours and further at 400-425 °C for 15 h. This was then pelletised (6 mm dia) and sized to -6+14 mesh size.

The reaction was carried out using a down flow, fixed bed, pyrex glass reactor of 20 mm I.D. The reactor was packed with 8.8 ml (13.2 g) Ti-PILC based catalyst. The reaction mixtures, 3-Picoline and water in the ratio 1:3 (by vol.) was fed at the rate 6.0 ml/h using a syringe pump (sage instrument). Ammonia gas (2.4 l/h) from gas cylinder and air (4.5 l/h) through calibrated flow meter were fed in to the reactor. The reaction was carried out at temperature of $430 \pm 10^{\circ}\text{C}$ and contact time 1.05. The product was cooled using ice cooled water and collected at the bottom followed by two number of ice traps. The product was analysed by gas chromatograph using 2 m length carbowax 20 M column at 160°C temperature and Thermal Conductivity Detector. The yield of 3- cyanopyridine obtained was 93.0 % the conversion 96.1 %.

The main advantages of the present invention are:

1. The catalyst is prepared in aqueous medium.
2. The said catalyst is active, stable and low cost material.

We claim:

1. A pillared clay based vanadia catalyst useful for the conversion of 3-picoline to 3-cyanopyridine, said catalyst comprising vanadium, phosphorous and molybdenum on a Ti-pillared clay support.
- 5 2. A catalyst as claimed in claim 1 wherein the clay is pillared with polyoxymetal cations of titanium and has titania clusters as the pillars between the layers.
3. A catalyst as claimed in claim 1 wherein the clay is selected from a single smectite clay and mixed layer smectite clays.
4. A catalyst as claimed in claim 3 wherein the single smectite clay comprises
10 montmorillonite clay.
5. A catalyst as claimed in claim 3 wherein the mixed layered smectite clay is selected from rectorite and paragonite.
6. A catalyst as claimed in claim 1 wherein the pillared clay contains one or more rare earth elements selected from cerium, lanthanum and a mixture thereof.
- 15 7. A catalyst as claimed in claim 1 wherein the ratio of the compounds of vanadium, molybdenum, phosphorous over titanium pillared clay in the catalyst is in a ratio ranging between 1.0: 2.5: 0.5: 20 - 1.0: 30: 1.5: 50.
8. A catalyst as claimed in claim 1 wherein the pillared clay contains a homogeneous
20 distribution of pillars in the interlayered spaces thereof forming an array of rectangular openings or pores of a size in the range of 7 to 20 Angstroms high and between 8 and 20 Angstroms wide, enabling the pillared clay to perform like a two-dimensional crystalline molecular sieve.
9. A process for the preparation of a pillared clay based vanadia catalyst comprising first
25 preparing vanadyl oxalate by heating a vanadium rich compound on a water bath followed by addition of oxalic acid till the colour of the mass changes to violet blue indicating the formation of vanadyl oxalate, said vanadyl oxalate being in dilute solution, adding a phosphorous source to the dilute solution of vanadyl oxalate heated over water bath, followed by addition of an aqueous solution of molybdenum source and mixing while adding a Titanium source under stirring, evaporating the solution over water bath
30 till the mass is reduced to about half, further heating the mass till a powder catalyst is obtained.
10. A process as claimed in claim 9 wherein the vanadium rich compound is selected from the group consisting of ammonium metavanadate, vanadyl sulphate and oxides of vanadium.

11. A process as claimed in claim 10 wherein the oxide of vanadium is vanadium pentoxide.
12. A process as claimed in claim 9 wherein the phosphorous source is selected from the group consisting of ortho-phosphoric acid, pyro-phosphoric acid and meta-phosphoric acid.
- 5 13. A process as claimed in claim 9 wherein the molybdenum source is ammonium molybdate.
14. A process as claimed in claim 9 wherein the titanium source is titanium-pillared clay.
15. A process as claimed in claim 14 wherein the clay is pillared with polyoxymetal cations of titanium and has titania clusters as the pillars between the layers.
- 10 16. A process as claimed in claim 14 wherein the clay is selected from a single smectite clay and mixed layer smectite clays.
17. A process as claimed in claim 16 wherein the single smectite clay comprises montmorillonite clay.
18. A process as claimed in claim 16 wherein the mixed layered smectite clay is selected
15 from rectorite and paragonite.
19. A process as claimed in claim 14 wherein the pillared clay contains one or more rare earth elements selected from cerium, lanthanum and a mixture thereof.
20. A process as claimed in claim 9 wherein the ratio of the compounds of vanadium, molybdenum, phosphorous over titanium pillared clay in the catalyst is in a ratio ranging
20 between 1.0: 2.5: 0.5: 20 - 1.0: 30: 1.5: 50.
21. A process as claimed in claim 9 wherein the reaction is carried out at a space velocity in the range of 1500 to 5500 h⁻¹ and after dilution of the catalyst with an inert medium to a range in the extent of 0.5 to 4 by volume with respect to the volume of catalyst.
22. A process as claimed in claim 9 wherein the reduced mass is heated at a temperature of
25 about 110⁰C in an air oven for 15 hours and then further heated in a muffle furnace at a temperature of about 300⁰C for 3 hours and subsequently at a temperature of about 425⁰C for 15 hours.
23. A process as claimed in claim 9 wherein the catalyst powder obtained is pelletized and sized to -6 to +14 mesh size.
- 30 24. A process as claimed in claim 9 wherein the vanadium rich compound comprises vanadium pentoxide, said process comprising heating vanadium pentoxide with water in the range of 1:3 to 1:5 (w/v) followed by addition of oxalic acid in the range of 2.5 to 3.0 parts by weight of vanadium pentoxide till the colour of the mass changes to violet blue; adding phosphorous source to the dilute solution of vanadyl oxalate in the range of 2 to 4

times by volume of vanadyl oxalate over heating bath at a temperature in the range of 70 to 80°C; preparing aqueous solution of molybdenum source in the range of 1:4 to 1:6 (w/v) and heating over a heating bath at a temperature in the range of 70 to 80°C; mixing both the solutions in heating condition over heating bath with appropriate amount of titanium-pillared clay under stirring; evaporating the mixture over a heating bath till the mass reduces to half; heating the mass in an air oven at a temperature in the range of 100 to 120°C for a time period in the range of 10 to 16 hours and in a muffle furnace at a temperature in the range of 250 to 350°C for a time period in the range of 16 to 20 hours and pelletizing the same size range of -6 to +14 BSS.

- 5 25. A process for the conversion of 3-picoline into 3-cyanopyridine in a single step, said process comprising reacting 3-picoline, ammonia and air in the presence of a Ti-pillared clay based vanadia catalyst to obtain 3-cyanopyridine, without requiring addition of oxidizing agents.
- 10 26. A process as claimed in claim 25 wherein the clay is pillared with polyoxymetal cations of titanium and has titania clusters as the pillars between the layers.
- 15 27. A process as claimed in claim 26 wherein the clay is selected from a single smectite clay and mixed layer smectite clays.
28. A process as claimed in claim 27 wherein the single smectite clay comprises montmorillonite clay.
- 20 29. A process as claimed in claim 27 wherein the mixed layered smectite clay is selected from rectorite and paragonite.
30. A process as claimed in claim 27 wherein the pillared clay contains one or more rare earth elements selected from cerium, lanthanum and a mixture thereof.
- 25 31. A process as claimed in claim 26 wherein the ratio of the compounds of vanadium, molybdenum, phosphorous over titanium pillared clay in the catalyst is in a ratio ranging between 1.0: 2.5: 0.5: 20 - 1.0: 30: 1.5: 50.
- 30 32. A process as claimed in claim 26 wherein the pillared clay contains a homogeneous distribution of pillars in the interlayered spaces thereof forming an array of rectangular openings or pores of a size in the range of 7 to 20 Angstroms high and between 8 and 20 Angstroms wide, enabling the pillared clay to perform like a two-dimensional crystalline molecular sieve.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IN 03/00101

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 7	B01J21/06	B01J21/16 B01J29/02 B01J27/18 C07D213/00
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC 7 B01J C07D		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the International search (name of data base and, where practical, search terms used)		
WPI Data, PAJ, EPO-Internal, COMPENDEX, INSPEC		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 970 659 A (ELION GLENN R ET AL) 20 July 1976 (1976-07-20) the whole document ----	
A	US 6 475 944 B1 (CHAE HO-JEONG ET AL) 5 November 2002 (2002-11-05) the whole document ----	
A	US 3 981 879 A (ELION GLENN R ET AL) 21 September 1976 (1976-09-21) the whole document ----	
A	US 2 861 999 A (D ALESSANDRO ALFRED F) 25 November 1958 (1958-11-25) the whole document ----- -/--	
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "Z" document member of the same patent family		
Date of the actual completion of the International search		Date of mailing of the international search report
10 February 2004		18/02/2004
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer de Cauwer, R

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IN 03/00101

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 2 510 605 A (ERCHAK JR MICHAEL ET AL) 6 June 1950 (1950-06-06) the whole document -----</p>	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IN 03/00101

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3970659	A	20-07-1976	NONE	
US 6475944	B1	05-11-2002	DE 10015696 A1	25-10-2001
US 3981879	A	21-09-1976	NONE	
US 2861999	A	25-11-1958	NONE	
US 2510605	A	06-06-1950	NONE	